SAFER G 53

TOP FEATURES

- Smooth bead appearance
- Slag removal similar to SAFER G 48 N with smoother arc.

CLASSIFICATION

AWS A5.1	E6013
EN ISO 2560-A	E 38 0 RC 11

TYPICAL APPLICATIONS

- Medium and light framework
- Tanks
- Tubular structures

WELDING POSITIONS

All positions

APPROVALS

ABS	LR	BV	DNV	TÜV
+	+	+	+	+

PACKAGING AND AVAILABLE SIZES

Diameter x Length (mm)	Packaging	Electrodes/pack	Net weight/pack (kg)	Item number
2.5 x 350	CBOX	240	4.4	W000258565
3.2 x 350	CBOX	170	4.7	W000258566
4.0 x 350	CBOX	115	5.0	W000258568

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:

Subject to Change – The information is accurate to the best of our knowledge at the time of printing.
Please refer to www.lincolnelectric.eu for any updated information.